

## Product Data Sheet

## Cebo ImprooFD®

## **Agriculture**

Cebo ImprooFD® is a specially selected, sodium-activated Bentonite. Cebo ImprooFD is produced under the GMP+ FSA B1 certification scheme and is therefore suitable for use in animal feed as an anti-caking agent, binder and substance for control of radionuclide contamination for all species (1m558i).

| Typical Properties |                                  |                                   |
|--------------------|----------------------------------|-----------------------------------|
| <u>Parameter</u>   | Test method / In accordance with | <u>Required</u>                   |
| Moisture content   | DIN 18121-1                      | Max. 12%                          |
| Grain size         | Sieve                            | Min. 95% < 125 $\mu$ m            |
| Specific density   | -                                | ≈ 2300 kg/m³                      |
| Bulk density       | -                                | ≈ 900 kg/m³                       |
| Colour             | -                                | Grey-beige                        |
| Form               | -                                | Powder                            |
| Odour              | -                                | Odourless                         |
| Composition        | -                                | <b>Activated Sodium Bentonite</b> |
| рН                 | -                                | 8-11                              |

In so far as we can ascertain, the above-stated information is correct. However, we are unable to provide any guarantees with regard to the results that you will achieve with this. This specification is provided on the condition that you determine yourself to what degree it is suitable for your purposes.

Cebo Holland BV Westerduinweg 1 NL-1976 BV IJmuiden The Netherlands

info@cebo.com www.cebo.com Tel. +31(0)255-546262

| Heavy metals according to the European guidelines |                                  |                                |  |  |
|---|----------------------------------|--------------------------------|--|--|
| <u>Parameter</u>                                  | Test method / In accordance with | Required / EU requirement*     |  |  |
| Arsenic (As)                                      | EN 15510                         | Max. 12 mg/kg (I.L.)           |  |  |
| Cadmium (Cd)                                      | EN 15510                         | Max. 2 mg/kg*                  |  |  |
| Fluor (F)   | by titrimetric method            | Max. 250 mg/kg (I.L.)          |  |  |
| Mercury (Hg)                                      | EN 16277                         | -                              |  |  |
| Lead (Pb)   | EN 15510                         | Max. 30 mg/kg* (28 mg/kg l.L.) |  |  |

| Chemical Properties            |                                  |                      |
|--------------------------------|----------------------------------|----------------------|
| <u>Parameter</u>               | Test method / In accordance with | <u>Typical value</u> |
| SiO <sub>2</sub>               | XRF                              | 45 - 55%             |
| $Al_2O_3$                      | XRF                              | 15 - 20%             |
| CaO                            | XRF                              | 5,0 - 10%            |
| Fe <sub>2</sub> O <sub>3</sub> | XRF                              | 2,0 - 5,0%           |
| MgO                            | XRF                              | 2,0 - 5,0%           |
| Na <sub>2</sub> O              | XRF                              | 1,0 - 4,0%           |
| SO <sub>3</sub>                | XRF                              | 1,0 - 3,0%           |
| K₂O                            | XRF                              | 0,5 - 2,0%           |
| Total Ash                      | ISO 11536 at 1025 C              | 80 - 93%             |

| Additive composition according to the European guidelines   |                                  |                              |  |  |
|---|----------------------------------|------------------------------|--|--|
| <u>Parameter</u>  | Test method / In accordance with | <u>Required</u>              |  |  |
| Dioctaeder montmorillonite                                  | EU 2019/1869                     | Min. 50% Smectite            |  |  |
| PCDD/PCDF (WHO-TE2005 LOQ incl.)                            | EU 2019/1869                     | Max. 0,75 ng/kg              |  |  |
| Dioxin-like PCB (WHO-TE2005 LOQ incl.)                      | EU 2019/1869                     | Max. 0,5 ng/kg               |  |  |
| Sum of PCDD/PCDF and Dioxin-like PCB (WHO-TE2005 LOQ incl.) | EU 2019/1869                     | Max. 1,5 ng/kg               |  |  |
| Sum of non dioxine-like PCB                                 | EU 2019/1869                     | <b>Max. 10</b> μ <b>g/kg</b> |  |  |
| Salmonella  | EU 142/2011                      | Not present                  |  |  |

## **Certification & Accreditation**

Cebo ImprooFD is delivered with a GMP+ FS B1 certificate, suitable for animal feed.



Cebo ImprooFD is available in 25 kg bags, 1000 kg Big Bags and as bulk.

Version; 09-2023

In so far as we can ascertain, the above-stated information is correct. However, we are unable to provide any guarantees with regard to the results that you will achieve with this. This specification is provided on the condition that you determine yourself to what degree it is suitable for your purposes.

Cebo Holland BV Westerduinweg 1 NL-1976 BV IJmuiden The Netherlands

info@cebo.com www.cebo.com Tel. +31(0)255-546262